

TECHNICAL DATA SHEET**TRENDY FLOOR****GENERAL DESCRIPTION:**

Trendy Floor Paint is a single pack high quality durable urethane floor coating with a gloss finish. Trendy Floor Paint is specially formulated to protect and decorate interior concrete floors, especially garage floors. It has excellent adhesion properties to concrete, good colour retention and is resistant to most acids and alkalis. Easy to clean with soap and water and has superior resistance to hot tyre pick-up.

USES:

For suitably prepared and primed interior concrete floors. eg. Garage Floors

FEATURES & BENEFITS:

- High durability
- Resistance to hot tyre pick up
- Ready for use
- Excellent adhesion
- Resistant to most acid and alkalis
- Water resistant

TECHNICAL INFORMATION**1. TRENDY FLOOR**

PHYSICAL FORM	Flammable viscous coloured liquid containing pigments
COLOUR	Range of standard colours
FINISH	Gloss, smooth
SPREADING RATE	Approximately 10m ² per litre per application
POLYMER TYPE	Urethane-modified resin
PIGMENTS	Oxides and durable types only
DRYING PROPERTIES	Surface or touch-dry: within 4 hours
RECOATING TIME	16h depending on conditions and film build
FLASH POINT	42°C (Contains flammable solvent)
PACKAGING	5L
THINNING	Use a minimum quantity of mineral turpentine if required
CLEANING	Equipment is readily cleaned using white spirits, brush cleaners, lacquer thinners etc. Cured paint may be removed using RB10 Paint Stripper or Aerosol Paint Stripper
APPLICATION METHOD	Supplied ready-for-use. Apply using Synthetic Enamel roller, brushing or spraying using conventional spray equipment (after dilution with mineral turpentine)

DO NOT PAINT

IF THE TEMPERATURE IS BELOW 10°C OR ABOVE 35°C
IF THE SURFACE IS DAMP (MOISTURE READING ABOVE 15%)
IF IT IS RAINING OR RAIN IS FORECAST
BEFORE 9H00 AND AFTER 16H00 IN THE WINTER

**B.DS.059
JP SERIES**

**RECOMMENDED APPLICATION PROCEDURE
SURFACE PREPARATION**

All surfaces must be dust free, clean, dry and free of any surface contamination or flaky paint. New or uncoated floor surfaces must be acid etched. (1Part Spirits of Salts with 5Parts Water) All traces of acid must be washed off with water. Dilute the first coat 10-15% by volume with Mineral Turpentine.

Previously coated surfaces must be well sanded to create a key for good adhesion.

HEALTH & SAFETY ADVICE

The product contains a flammable solvent. Precaution must be taken to prevent naked flames coming in contact with vapours (i.e. smoking must be prohibited). Solvents may also cause narcotic effects if the vapour concentration is too high: always ensure adequate ventilation (do not use solvent based paints in a poorly ventilated or closed space). Avoid contact with skin, eyes, mouth etc. Wear protective clothing, goggles & gloves. If body contact is made, rinse off immediately. Wash product off skin before it has dried using soap and water.

DISCLAIMER ADVICE

The information given in this Product Information Sheet is based on controlled laboratory tests and many years of experience. It is given in good faith but no guarantee of any performance characteristic is given or implied. Promac Paints cannot be held liable for consequential damage of whatsoever nature that may arise from the use of Promac products. Paint technology is continuously being developed and Promac Paints reserves the right to update product specifications without prior notice. Contact Promac Paints for further details.